


# YKK AP Standard Paint Colors



**Bone White V391A453**



**Colonial White V391A500**



**Sandstone V393X321**



**Beige V393F061**



**Seawolf Beige V397F199**



**Aged Copper V395F502**




**Hartford Green V395F518**



**Regal Blue V396F276**



**Colonial Red V394F170**




**Boysenberry V394F120**




**Fashion Gray V392F217**



**Charcoal V392F232**



**Classic Bronze V397X418**



**Black V378X500**



The 70% PVDF (Kynar 500® or Hylar 5000®) two-coat, non-exotic, non-metallic colors shown on this page are reproduced as closely as possible to the actual colors and are to be used only as a guide. These 14 colors are available on YKK AP's **Express Service Program**, and may be estimated using the list prices in the current YKK AP Price Book. Additional colors and finishes are available. Contact your local sales representative for pricing, lead time information, and actual sample panels.

Kynar 500® is a registered trademark of Arkema, Inc. Hylar 5000® is a registered trademark of Solvay Solexis, Inc.

Printed in the U.S.A.

---

**YKK AP  
America Inc.****Atlanta**  
8140 Troon Circle  
Suite 110  
Austell, GA 30168  
Tel: 678-945-6190  
Fax: 678-945-6328**Boston**  
Eight Connector Road  
Andover, MA 01810  
Tel: 978-749-9554  
Fax: 978-749-2915**Baltimore**  
8680 Greenwood Place  
Savage, MD 20763  
Tel: 301-498-3650  
Fax: 301-498-3755**Chicago**  
1000 Stevenson Court  
Suite 100  
Roselle, IL 60172-4314  
Tel: 630-582-9602  
Fax: 866-955-2441**Cincinnati**  
5406 Spellmire Drive  
Cincinnati, OH 45246  
Tel: 513-942-7200  
Fax: 513-682-2123**Dallas**  
2025 W. Belt Line Road  
Suite 130  
Carrollton, TX 75006  
Tel: 972-245-9551  
Fax: 972-245-9522**Greensboro**  
4524 Green Point Drive  
Suite 106  
Greensboro, NC 27410  
Tel: 336-665-1963  
Fax: 336-665-1965**Houston**  
3550 Brittmoore Road  
Suite 200  
Houston, TX. 77043  
Tel: 713 329-9551  
Fax: 713 939-0811**Orlando**  
7608 Currency Drive  
Orlando, FL 32809  
Tel: 407-856-0660  
Fax: 407-856-0090**Headquarters**  
7680 The Bluffs  
Suite 100  
Austell, GA 30168  
Tel: 678-838-6000  
Fax: 678-838-6001**AAMA 2605  
Specifications**

Description	Coating Requirements
<b>Color Uniformity</b>	Visual control
<b>Specular Gloss at 60°, ASTM D 253</b>	Medium and low gloss ranges
<b>Dry Film Hardness, ASTM D 3363</b>	F minimum
<b>Film Adhesion (Dry, Wet and Boiling Water), Crosshatch</b>	No removal between scribed lines
<b>Impact Resistance (Direct) 0.10" Distortion</b>	No removal of film
<b>Chemical Resistance (10% Muriatic Acid)</b>	15 minutes, no visual changes
<b>Chemical Resistance (Mortar, Alkali)</b>	24 hours, no visual changes
<b>Resistance to Acid Pollutants (70% Nitric Acid)</b>	30 minutes, maximum 5rE Hunter units color change, not applicable for micas or metallics
<b>Detergent Resistance</b>	72 hours, no effect
<b>Humidity Resistance, ASTM B 2247</b>	4000 hours, few #8 blisters (maximum)
<b>Salt Spray Resistance, ASTM B 117</b>	4000 hours, minimum 7 rating on scribe and minimum blister rating of 8 (ASTM D 1654)
<b>Weathering, Color Retention, ASTM D 2244</b>	10 years, 45° South Florida, maximum 5rE Hunter units color change, not applicable for micas or metallics
<b>Weathering, Chalk Resistance ASTM D 4214</b>	10 years, 45° South Florida, maximum 8 for colors, 6 rating for whites
<b>Weathering, Erosion Resistance</b>	10 years, 45° South Florida, maximum 10% loss

For further information, please contact your local YKK AP Sales Office above, call **1-800-955-9551** and ask for an architectural sales representative, or visit us at [www.ykkap.com](http://www.ykkap.com).

---